



PB10102

DESCRIPTION

Compression molded 15% carbon filled PolyTetraFluoroEthylene (PTFE).

TYPICAL PROPERTIES

Property	Test Method	Units	Typical Value
Color	-	-	Black
Specific Gravity	ASTM D792	-	2.11
Hardness Shore D	ASTM D2240	Shore D	68 _(peak)
Tensile Strength	ASTM D4745	PSI [MPa]	2,725 [19]
Elongation at Break	ASTM D4745	%	150

REQUIREMENTS

N/A