



PB21000M

DESCRIPTION

Compression molded virgin Poly(Fluorinated Ethylene-Propylene) copolymer (FEP).

TYPICAL PROPERTIES

Property	Test Method	Units	Typical Value
Color			Translucent to White
Specific Gravity	ASTM D792		2.15
Hardness Shore D	ASTM D2240	Shore D	64
Tensile Strength	ASTM D2116	PSI [MPa]	4,150 [29]
Elongation at Break	ASTM D2116	%	340

REQUIREMENTS

This product meets ASTM D2116 Type III requirements.